

1: Specifications:

A. Chemical Composition (on dry basis, percentage by weight)

Guaranteed

Fe (Fe ₂ O ₃)	64.50% basis, 63.5% below rejection.
SiO ₂	3.00% Max
TiO ₂	0.30% Max
Al ₂ O ₃	0.50% Max
MnO	0.20% Max
MgO	0.60% Max
Na ₂ O	0.10% Max
K ₂ O	0.05% Max
P ₂ O ₅	0.05% Max
P	0.06% Max
S	0.035% Max
CaO	0.20% Max

B. Moisture Content (Free moisture loss at 105 degrees centigrade)

Guaranteed Maximum 8.00% Max

C. Physical Specification (Natural Basis): 10 mm nominal

Fines: or as agree to in the contract

Guaranteed *Below 10 mm- 90% min. as a load basis set by seller*